

To Clean or Not to Clean: Managing Fouling on Boat Hulls

Boat owners must control hull fouling to maintain vessel speed and fuel efficiency. Widely used, copper-based, antifouling paints initially slow fouling on boat hulls due to their toxic nature, although some invasive species can grow on hulls coated with copper antifoulants.⁶ These toxic paints face restrictions in California and possibly elsewhere due to water quality concerns.^{1,3,7a,7b} Thus, nontoxic and less-toxic hull coatings will likely become more common. As a result, companion strategies, such as in-water hull cleaning, are also needed to control hull fouling.

However, Australian research suggests that in-water hull cleaning practices may stimulate fouling growth.⁴ This research used cleaning practices that are quite different than those used in California. Thus, we conducted research to assess responses of fouling growth to best management practices (BMPs) developed and used by the California Professional Divers Association (CPDA).

Evaluating California Hull Cleaning BMPs

We conducted our study at three locations: Santa Barbara Harbor and the inner and outer ends of Shelter Island Yacht Basin of San Diego Bay. The study occurred in 2008 from June through September when fouling is typically heaviest.

Experimental panels were submerged at local boat docks. Each panel had a base gel-coating. On top of the gel coating one of the following products was applied: copper antifouling paint; nontoxic ceramic-epoxy; or nontoxic, siliconized epoxy. We had three cleaning treatments: continuously cleaned; cleaned once; and not cleaned (new).



“Continuously cleaned” panels were cleaned in water for three months using California BMPs. “Cleaned once” panels were cleaned only at the end of three months. Then, both sets of panels were redeployed for a fourth month, and a set of new “not cleaned” panels was added.

Before each cleaning, we rated the fouling present on each panel and the cleaning tool and effort required to remove it, using a five-point scale developed with the CPDA.^{2,5} At the end of the fourth month, all panels were cleaned and the levels of fouling growth, cleaning tool and cleaning effort were recorded along with the weight of the removed fouling growth.



To Clean or Not to Clean: California BMPs

Results of our study indicate that the in-water hull cleaning BMPs of the CPDA are an effective companion strategy for managing fouling on boat hull-coatings. We found:

- There was no significant difference in amount of fouling among cleaning treatments.
- Slightly more abrasive tools and cleaning effort were required for the nontoxic-coated panels and for panels that had been cleaned (either once or continually).
- Panels with copper-based antifoulants were far less fouled than panels with nontoxic coatings, as expected for new, copper-based antifoulants.
- The amount of fouling was significantly less at the northern location (Santa Barbara) than at the two southern locations (San Diego).

Why the difference from Australian results?

We used California BMPs that employ frequent, gentle cleaning to protect the hull coating and to prevent fouling from maturing and accumulating to the point that aggressive tools and intense effort are needed.² In contrast, longer cleaning intervals were used in the Australian research and this allowed fouling organisms to mature and some to become tougher or harder. A more aggressive tool and greater effort were required to

remove the older fouling organisms, resulting in scratching and/or chipping of the coating and leaving fragments of fouling organisms. Scraped surfaces with

remains of fouling organisms greatly enhanced settlement.⁴

Conclusions

Our results support using nontoxic coatings with in-water hull cleaning BMPs of California to co-manage water quality and invasive species. Frequent cleaning with the gentlest, effective cleaning tool and level of effort on a schedule that is suitable for the amount of fouling in a given location and time of year should improve fouling control without stimulating the next generation of fouling growth. These findings have implications for developing fouling control policies that are environmentally and cost-effective.



References Cited

1. California Department of Pesticide Regulation. 2010. Notice of Decision to Initiate Reevaluation of Copper Based Antifouling Paint Pesticides. California Notice 2010-03. www.cdpr.ca.gov/docs/registration/canot/2010/ca2010-03.pdf Accessed July 15, 2010.
2. California Professional Divers Association. 2008. Best Management Practices Certification Manual. April 5, 2008. 118 pp.
3. California Regional Water Quality Control Board, San Diego Region. 2006. Shelter Island Yacht Basin TMDL for Dissolved Copper. <http://www.waterboards.ca.gov/sandiego/tmdls/shelter%20island.html>. Accessed August 29, 2006.
4. Floerl, O. 2002. Intracoastal Spread of Fouling Organisms by Recreational Vessels. Thesis submitted for the degree of Doctor of Philosophy. School of Tropical Environment Studies and Geography. James Cook University, Townsville, Australia.
5. Johnson, L.T. and J.A. Gonzalez. 2004. Staying Afloat with Nontoxic Antifouling Strategies for Boats. California Sea Grant College Program Report No. T-054.

6. Piola, R.F., K.A. Dafforn and E.L. Johnston. 2009. The influence of antifouling practices on marine invasions. *Biofouling* 25(7):633-644.

7a. State of Washington 62nd Legislature. 2011. House Bill 1785. An Act relating to limiting the use of certain antifouling paints; adding a new chapter to Title 70 RCW; and prescribing penalties.

<http://apps.leg.wa.gov/billinfo/summary.aspx?year=2011&bill=1785#documents> Accessed February 15, 2011.

7b. State of Washington 62nd Legislature. 2011. 7b. Substitute Senate Bill 5436. An Act relating to the use of antifouling paints on recreational water vessels; adding a new chapter to Title 70 RCW; and prescribing penalties.

<http://apps.leg.wa.gov/billinfo/summary.aspx?bill=5436&year=2011> Accessed February 15, 2011.

Acknowledgments This publication is based upon scientific work conducted by L.T. Johnson, C.S. Culver, H.M. Page and J.E. Dugan. We gratefully acknowledge the marina and harbor authorities, who allowed us to work in their facilities. The research and this publication were supported in part by the California Department of Boating and Waterways Project No. 07-106-111, NOAA Grants Nos. NA10OAR4170060, NA08OAR4170669 and NA04OAR4170038, California Sea Grant Project No. A/EA-1 through NOAA's National Sea Grant College Program, U.S. Dept. of Commerce; University of California Agriculture and Natural Resources; University of California Cooperative Extension; California Resources Agency; and Counties of San Diego, Santa Barbara and Ventura, and the Marine Science Institute, University of California Santa Barbara. The statements, findings and conclusions in this report are those of the authors and not necessarily those of the sponsors. The mention of commercial products, their source, or their use in connection with material reported herein is not to be construed as actual or implied endorsement of such products.

The University of California Division of Agriculture & Natural Resources (ANR) prohibits discrimination or harassment of any person in any of its programs or activities (Complete nondiscrimination policy statement can be found at <http://ucanr.org/sites/anrstaff/files/107734.doc>)

Inquiries regarding ANR's equal employment opportunity policies may be directed to Linda Marie Manton, Affirmative Action Contact, University of California, Davis, Agriculture and Natural Resources, One Shields Avenue, Davis, CA 95616, (530) 752-0495.

Leigh Johnson, Coastal Resources Advisor, University of California Cooperative Extension;

Carolynn Culver, California Sea Grant Advisor, University of California; and

Scott Parker, Program Representative, University of California Cooperative Extension

**UCCE-SD/UC-SGEP Fact Sheet 2011-3
February 2011 (rev. September 2011)**

<http://ucanr.org/coast>

<http://cesandiego.ucdavis.edu>

